



UNSTOPPABLE PROTECTION EASILY DUPLICATE FINE TO COARSE TEXTURES

Two-component, urethane, textured coating for the ultimate protection of lower panels prone to chipping and corrosion.

- OEM recommended
- Topcoat with solvent or waterborne systems
- Tintable to match OEM colors

- Best-in-class protection
- Duplicate most OEM textures
- Excellent gloss retention



PART NO: 40820

TWO-COMPONENT KIT CONTAINS:

1 – 40824 | Pro-Tex 2K Chip Guard | Quart

2 - 40836 | Catalyst | Half Pint



STEP 1

PRFP

Clean with Scuff & Clean and gray scuff pad. Rinse with water and dry. Clean with **SEM Solve** or **XXX Universal Surface Cleaner.** Wipe clean in one direction with clean, lint-free cloth.

Sand with P180 - P220 grit sandpaper. Re-clean with **SEM Solve or XXX Universal Surface Cleaner.** Wipe clean in one direction with clean, lint-free cloth.

- (i) "Back-taping" helps eliminate any heavy edges and provides smooth transition to other surfaces.
- Prime bare metal with a direct to metal epoxy or 2K urethane primer. Allow primer to fully cure.



SEM Solve

A virgin solvent blend to clean panels prior to refinish or repair.

| Part | Size |
|-------|----------------|
| 38371 | Gallon |
| 38373 | 20 oz. Aerosol |
| 38374 | Quart |
| | |



XXX Universal Surface Cleaner

A super compliant, waterborne cleaner that removes solvent and water soluble contaminants prior to refinishing.

| Part | Size | |
|-------|--------|--|
| 77771 | Gallon | |
| 77774 | Quart | |

STEP 2 MIX

If tinting, mix 8 parts Pro-Tex 2K Chip Guard to 1 part solvent-based colorant. Mix 2 parts tinted mixture to 1 part Pro-Tex 2K Chip Guard Catalyst. Stir well.

Use only automotive solvent-based paint without any binders or reducers - color only. Do not use water-based or lacquer-based colorants.

Note: Spray test panel to verify color before use. Adjust color as necessary. Do not catalyze more than 1 quart at a time. Pot life is 20 minutes at 70°F. High heat and humidity may significantly reduce pot time.



Pro-Tex 2k Chip Guard Kit

A two-component urethane textured coating for the ultimate protection of lower panels prone to chipping and corrosion.

| 40820 kit contains: | | | | |
|---------------------|-----------|------|--|--|
| Part | Size | Qty. | | |
| 40824 | Quart | 1 | | |
| 40836 | Half Pint | 2 | | |

STEP 3 APPLY

Pour contents into desired spray equipment. For OEM textures, use a gun equipped with a 1.8 mm - 2.2 mm nozzle. For a more heavy textured finish, use Premium **Undercoat Applicator**. Recommended air pressure is 45 – 90 psi.

Apply 2 coats, allowing 10 – 20 minutes flash time between coats.

Remove all masking tape while the final coat is still wet. It can be topcoated after 30 minutes.

Clean spray equipment immediately after use. Use XXX Universal Gun Cleaner or material compliant with VOC regulations in your area.

Related Products



Premium **Undercoat Applicator**

A siphon feed heavy plastic applicator for spraying bed liners, undercoating and rust proofing.

| | Docorribation. |
|-------|----------------|
| 71109 | Applicator |
| | |
| | |
| | |

Part

Description



XXX Universal Gun Cleaner

Quickly removes solvent-based and waterborne coatings from spray equipment.

| Part | Size |
|-------|----------------|
| 77763 | 20 oz. Aerosol |









UNSTOPPABLE PROTECTION

A TWO-COMPONENT URETHANE TEXTURED COATING FOR LOWER PANELS PRONE TO CHIPPING AND CORROSION

- OEM Recommended
- Tintable and paintable
- Duplicate all OEM textures
- Topcoat with solvent or waterborne systems
- Best in class protection
- No special equipment needed
- Excellent gloss retention

40820 KIT CONTAINS:

- 1 40824 | PRO-TEX 2K CHIP GUARD | Quart
- 2 40836 | Catalyst | Half Pint



FROM FINE TO HEAVY TEXTURE, SEM PRO-TEX 2K CHIP GUARD IS THE RIGHT PRODUCT FOR THE JOB







A TWO-COMPONENT URETHANE TEXTURED COATING

FOR LOWER PANELS PRONE TO CHIPPING AND CORROSION

- OEM Recommended
- Tintable and paintable
- Duplicate all OEM textures
- Topcoat with solvent or waterborne systems
- Best in class protection
- No special equipment needed
- Excellent gloss retention

40820 KIT CONTAINS:

- 1 40824 PRO-TEX 2K CHIP GUARD Quart
- 2 40836 | Catalyst | Half Pint



FROM FINE TO HEAVY TEXTURE, SEM PRO-TEX 2K CHIP GUARD IS THE RIGHT PRODUCT FOR THE JOB

